


Numerous application possibilities with NedZink NOVA COMPOSITE

NedZink NOVA COMPOSITE




Product description

NedZink's NOVA COMPOSITE gives the qualities of zinc an extra dimension. Its many talents lend themselves to new ideas in façades, roofs and interiors. With a layer of polyethylene between two layers of zinc, NOVA COMPOSITE can be easily processed with standard tools, routed into cassettes or simply screwed or riveted into position. Self-coloured, rigid and extremely stable - enabling untold applications of zinc.


NOVA COMPOSITE opens the way to new ideas, new forms, new structures, a new drive. The very special character of zinc captures the properties of a new and practical building material. NOVA COMPOSITE is ideal as a maintenance-free material that stands up to the elements superbly. The strength and stability of the panels are a major advantage. This, combined with the elegant appearance of the prepainted zinc, produces a product of exceptional quality and appearance.

NedZink NOVA COMPOSITE can be applied to large façade coverings without any wave formation. Even panels of 1,000 x 6,000 mm can be applied. Rounded elements and forms are easily realized. Given the appearance and versatility of the product the opportunities for creative design are endless.


Thanks to this new development, NedZink has clearly expanded the possibilities of titanium zinc façade covering and offers architects, developers and craftsmen a product that is suitable for a wide range of different possibilities.




Adhering



Clamping



Mechanical screw fixed



Hook-on system

The following attachment methods are possible with this NOVA Composite:

- Adhering
- Clamping
- Mechanical screw fixed
- Hook-on system

Technical characteristics NedZink NOVA COMPOSITE:		
standard dimensions	3200 x 1000 mm	
standard panel strength	4 mm	
panel composition	on top and at the bottom	: 2 x 0,5 mm NedZink NOVA
	core	: 3 mm Polyethylen - low density (LDPE)
tolerances	thickness	: -0 / +0,4 mm
	width	: + / -2,0 mm
	length	: -0 / +4,0 mm
	diagonal	: max 3,0 mm

Transport and storage

NedZink products are packed and sent dry. The advice is to store titanium zinc dry and in a constant as possible temperature. This reduces the probability of condensation formation.

Surface

NedZink NOVA COMPOSITE is supplied with a foil on the surface to protect the surface during transport and assembly. This foil should be removed immediately and in one smooth motion after assembly at the construction site. Mechanical deformation of zinc below 7°C material temperature (and removal of the protective foil) is not allowed.

The products supplied when incorporated within any system, compliant with the suppliers guidelines for processing and installation, will remain water impervious and not perforate due to manufacturing defects.

For additional information about the product range and the processing of NedZink products, see our website **www.nedzink.com**.



Netherlands

NedZink B.V.
Postbus 2135, NL-6020 AC Budel
Hoofdstraat 1, NL-6024 AA Budel-Dorplein
Tel: +31 (0)495-455700
Fax: +31 (0)495-455790
www.nedzink.com | info@nedzink.com

Germany

NedZink GmbH
Im Lipperfeld 21
D-46047 Oberhausen
Tel: +49 (0)208-85798-0
Fax: +49 (0)208-85798-30
www.nedzink.de | info@nedzink.de

Belgium

NedZink n.v.
Avenue Jean Lenoir 14
B-1348 Ottignies (Louvain-la-Neuve)
Tel: +32 (0)10-452727
Fax: +32 (0)10-453362
www.nedzink.be | info@nedzink.be

France

NedZink SAS
1, rue François Jacob
FR-92500 Rueil-Malmaison
Tel : +33 (0)6-45 69 02 49
www.nedzink.fr | info@nedzink.fr



NedZink trademarks

NedZink® NATUREL, NedZink® NOVA, NedZink® NOIR, NedZink® NUANCE, NedZink® Pro-Tec, NedZink® NOVA STRUCTURE, NedZink® NOVA COMPOSITE and NTZ®

Liability

This brochure was produced with the utmost care. All information specified in this brochure is according to our current knowledge, and gives information about our products and their uses. It is not, however, intended as a guarantee for certain properties of the products or their suitability for an actual application. One can therefore derive no rights from the content of this brochure.